



A M B I A N C E S A V I A T I O N

AMB 325 FABRIC

Composition	100% Polyester fire retardant
Masse	380 gr/sqm ²
Width	160 cm
Washing Fastness - ISO 105 C06	40°C 4* 60°C 4*
Shade Change - ISO 105 C06	40°C 5* 60°C 5*
Light Fastness - ISO 105 B02	4.5* after 150hours
Tear Strenght - ISO 13934-1	Warp 242 daN Weft 195 daN
Seam Strenght - ISO 13936	Warp 13 daN Weft 11 daN
Pilling test - ISO 12945-2	4* during 5hours 4* during 10hours
Abrasion resistance - ISO 12947-2	97 900 cycles
Fire test	CS/JAR/FAR 25.853 App. F - Flammability FAR 25.853 App. F Part II - Seat Cushion FAR 25.853 App. F Part IV - Heat Release ABD 0031 Issue F - Smoke Density ABD 0031 Issue F - Toxicity

*5 scale

Available colours following customers requests
Embossing customizable
Minimum purchase order per 200ml
Delivery within 3 weeks