



A M B I A N C E S A V I A T I O N

AMB CUSTOM LEATHER

Average Skin Surface 5 sqm

Standard Weight 900 g/sqm

Light Weight 700 g/sqm

Tanning Chromium tanned

Dyeing Deeply

Fireproofing During tanning

Leather Types Pigmented - Corrected Grain

Thickness 1.0 - 1.2 mm

PH - DIN 53312 > 3.5

Flex Resistance - EN 13334 No cracks after 20 000 cycles

Wet-Rubbing - ISO 11640 ≥ 5 after 200 cycles

Dry-Rubbing - ISO 11640 ≥ 5 after 1 000 cycles

Light Fastness - ISO 105-B02 ≥ 5

Tear Strenght - DIN 53329 ≥ 25 N

Tensile Strenght - DIN 533328 ≥ 80 N

Adhesive Strenght - IUF 470 ≥ 5 N

Determination of Abration Resistance - DIN 53109 No damage CS10 wheels, 500g after 3 500 cycles

Fire test CS/JAR/FAR 25.853 App. F Part I.(a1)(ii) - Flammability

FAR 25.853 (d) App. F Part IV - Heat Release

ABD 0031 Issue F - Smoke Density

ABD 0031 Issue F - Toxicity

Available colours following customers requests

Cutting parts on request

Minimum purchase order per 50 m²

Delivery within 5 weeks

HAMEAU D'ANDREVILLIERS F-28190 SAINT-GEORGES-SUR-EURE TEL. +33 (0)2 37 26 84 63 FAX +33 (0)2 37 26 86 15
ambiances@ambiances-aviation.com www.ambiances-aviation.com

SARL AU CAPITAL SOCIAL DE 30 500 € - APE 4614Z—TVA FR 64 639 802 867