



A M B I A N C E S A V I A T I O N

AMB FIRST LEATHER

Skin Surface 5sqm

Weight 900 gr/sqm

Tanning Chromium tanned

Dyeing Deeply

Fireproofing During tanning

Leather Types Pigmented—Corrected Grain—Trough Dyeing Aniline

Thickness 1.0 - 1.2 mm

Dry Rub fFastness - ISO 11640 ≥ 4 on Grey Scale after 2 000 cycles
 ≥ 4 on Grey Scale after 500 cycles

Fastness to Light - ISO 105-B02 ≥ 6 on Blue Scale

Adhesion of Finish - ISO 11644 ≥ 2 N / 10mm

Tear Strenght - ISO 3377-1 ≥ 20 N

Flex Resistance - ISO 5402-1 No cracks after 50 000 cycles

Determination of Abration Resistance - ISO 17076-1 No damage CS10_500gr after 2 000 cycles

Fire test CS/JAR/FAR 25.853 App. F Part I.(a1)(ii) ABD 0031
Issue F & AITM 2.0002B - Vertical Bunsen Burner Test
12s Ignittion Time

Available Colors in Stock
Cutting parts on request
Minimum purchase order per 10m²
Delivery within 2 weeks